

Claims

1 A product comprising man-made vitreous fibres formed of a composition which includes, by weight of oxides,

SiO ₂	32 to 48%
Al ₂ O ₃	18 to 30%
CaO	10 to 30%
MgO	2 to 20%
FeO	2 to 15%
Na ₂ O + K ₂ O	0 to 10%
TiO ₂	0 to 6%
Other Elements	0 to 15%

and the composition has a viscosity at 1400°C of 10 to 70 poise,

and the fibres have a dissolution rate of at least 20nm per day when measured at a pH of 4.5.

10026491-122401

sub A₁ >

sub A₂ >